

アイビーム

一般構造用圧延鋼材 SS400 JIS G3101(1987)

アイビーム

kg/本

サイズ A×B	厚さ		1.0	5.5	6.0	7.0	8.0	9.0	10.0	11.0	12.0
	t1	t2									
100×75	5	8	12.9	71.0	77.4	90.3	103	116	129	142	155
125×75	5.5	9.5	16.1	88.6	96.6	113	129	145	161	177	193
150×75	5.5	9.5	17.1	94.0	103	120	137	154	171	188	205
150×125	8.5	14	36.2	199	217	253	290	326	362	398	434
180×100	6	10	23.6	130	142	165	189	212	236	260	283
200×100	7	10	26.0	143	156	182	208	234	260	286	312
200×150	9	16	50.4	277	302	353	403	454	504	554	605
250×125	7.5	11.5	38.3	211	230	268	306	345	383	421	460
	10	19	55.5	305	333	388	444	500	555	610	666
300×150	8	13	48.3	266	290	338	386	435	483	531	580
	10	18.5	65.5	360	393	458	524	590	655	720	786
	11.5	22	76.8	422	461	538	614	691	768	845	922
350×150	9	15	58.5	322	351	410	468	526	585	644	702
	12	24	87.2	480	523	610	698	785	872	959	1,046
400×150	10	18	72.0	396	432	504	576	648	720	792	864
	12.5	25	95.8	527	575	671	766	862	958	1,054	1,150
450×175	11	20	91.7	504	550	642	734	825	917	1,009	1,100
	13	26	115	632	690	805	920	1,035	1,150	1,265	1,380
600×190	13	25	133	732	798	931	1,064	1,197	1,330	1,463	1,596
	16	35	176	968	1,056	1,232	1,408	1,584	1,760	1,936	2,112